



UPDATED: 12.17.2015

ACFOAM®-III INSULATION

PRODUCT DATA SHEET

- DESCRIPTION:** Closed-cell polyisocyanurate (polyiso) foam core integrally bonded to inorganic coated glass facers. ACFoam®-III is offered in a variety of thicknesses, providing long-term thermal resistance (LTR) values from 5.7 to 26.8. Available in 4ft x 8ft (1220mm x 2440mm) and 4ft x 4ft (1220mm x 1220mm) panels. Manufactured in accordance with **ASTM C1289, Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi) and CAN/ULC-S704 Type 2, Class 3 or Type 3, Class 3.**
- ADVANTAGES:** When using ACFoam®-III in adhered systems, field testing has confirmed significantly more efficient use of solvent-based adhesives than with organic faced insulation. Adhesive application rates vary by manufacturer. Check adhesive manufacturer's recommendation for application rates. Manufactured using CFC-, HCFC- and HFC-free foam blowing technology with zero ozone depletion potential (ODP) and virtually no (negligible) global warming potential (GWP). Recognized by the GREENGUARD Environmental Institute as resistant or highly resistant to mold growth based on independent testing using GREENGUARD Test Method GGTM.P040 (ASTM D6329) for microbial resistance. ACFoam®-III contains between 11.2% and 6.2% recycled materials by weight (*Atlas Technical Bulletin: TB-2*). Class A ratings can be achieved with ACFoam®-III when the total insulation thickness is a minimum of 3.0" and placed directly on a combustible deck (1/2:12 maximum deck slope).
- APPLICATION:** Manufactured and tested for use in new and re-roofing applications. ACFoam®-III is used in built-up (BUR), modified bitumen, metal, ballasted single-ply, mechanically attached single-ply and adhered single-ply roofing systems. These roofing systems depend on proper installation for successful performance. Refer to FM Approvals® RoofNav and UL Online Certifications Directory for additional application details.
- INSTALLATION:** ACFoam®-III shall be kept dry before, during and after installation. This product will burn if exposed to an ignition source of sufficient heat and intensity. Do not apply flame directly to ACFoam®-III insulation. Refer to product packaging and PIMA Technical Bulletin #109 for storage and handling recommendations. **An offset or staggered multi-layer application of ACFoam® is strongly recommended when the total insulation thickness exceeds 2.7"** (*Atlas Technical Bulletin: TB-5*). Typical field fastening requirements can be obtained from membrane system manufacturer or FM Global Property Loss Prevention Data Sheets 1-29.

Prior to installation, Atlas Roofing Corporation recommends that you consult your local building codes, contract documents, professional engineer, FM Global, Miami-Dade County and membrane manufacturer for additional installation guidelines as well as design enhancements.

PHYSICAL PROPERTIES

| PROPERTY | TEST METHOD | RESULTS |
|--------------------------|--------------------|--------------------------------------|
| DIMENSIONAL STABILITY | ASTM D2126 | < 2% |
| COMPRESSIVE STRENGTH | ASTM D1621 | 20 psi (140 kPa) or 25 psi (172 kPa) |
| WATER ABSORPTION | ASTM C209 & D2842 | < 1.5%, < 3.5% |
| WATER VAPOR TRANSMISSION | ASTM E96 | < 4.0 perm (228.8ng/(Pa*s*m²)) |
| PRODUCT DENSITY | ASTM D1622 | Nominal 2.0 pcf (32.04 kg/m³) |
| FLAME SPREAD | ASTM E84 (10 min.) | 140-60 |
| SMOKE DEVELOPMENT | ASTM E84 (10 min.) | 150-170 |
| TENSILE STRENGTH | ASTM D1623 | > 730 psf (35 kPa) |
| SERVICE TEMPERATURE | - | -100° to +250°F |

¹Numerical ratings are not intended to reflect performance under actual fire conditions. Flame spread index of ≤ 75 and smoke development ≤ 450 meet code requirements for foam plastic roof insulation. Codes exempt foam plastic insulation when used in FM 4450 or UL 1256. Physical properties listed above are presented as typical average values as determined by accepted ASTM test methods and are subject to normal manufacturing variation.

THERMAL DATA

| LTR VALUE | THICKNESS | | ²RSI | FLUTE SPANABILITY | |
|-----------|-----------|-------|------|-------------------|--------|
| | in | mm | | in | mm |
| 5.7 | 1.0 | 25.4 | 1.00 | 2.625 | 66.68 |
| 8.6 | 1.5 | 38.1 | 1.50 | 4.375 | 111.13 |
| 11.4 | 2.0 | 50.8 | 2.01 | 4.375 | 111.13 |
| 14.4 | 2.5 | 63.5 | 2.53 | 4.375 | 111.13 |
| 17.4 | *3.0 | 76.2 | 3.06 | 4.375 | 111.13 |
| 20.5 | *3.5 | 88.9 | 3.60 | 4.375 | 111.13 |
| 23.6 | *4.0 | 101.6 | 4.15 | 4.375 | 111.13 |

LTR (long term thermal resistance) values were determined in accordance with CAN/ULC-S770-09. Test samples were third-party selected and tested by an accredited material testing laboratory. The LTR results were reviewed by FM Global and certified by the PIMA Quality Mark Program. ²RSI is the metric expression of R-value (m² • K/W).

*To minimize the effects of thermal bridging, Atlas strongly recommends the use of multiple layers when the total desired or specified R-value requires an insulation thickness greater than 2.7" thick.

- **ASTM C1289, Type II, Class 2, Grade 2 (20 psi) or Grade 3 (25 psi)**
- **CAN/ULC-S704, Type 2, Class 3 or Type 3, Class 3**
- **CCMC No. 12423-L**
- **UL Certified for Canada— Insulated Roof Deck Assemblies Construction No. C38 and 52. Meet CAN/ULC-S126, CAN/ULC-S101 and CAN/ULC-S107**
- **UL Standard 1256 Classification Construction No. 120, 123 & 292**
- **UL Standard 790 (ASTM E108) Roofing Systems Classification**
- **UL Standard 263 (ASTM E119) Fire Resistance Classification**
- **UL Standard 1897 Uplift Resistance**
- **FM Standard 4450/4470 Approved**
Refer to FM Approvals® RoofNav for Specific System Details
- **IBC Chapter 26 & NBC Sections on Foam Insulation**
- **California State Insulation Quality Standards and Title 25 Foam Flammability Criteria (T 1231)**
- **Miami-Dade County Approved**
- **State of Florida Product Approval (FL17989)**

Other than the aforementioned representations and descriptions, Atlas Roofing Corporation (hereafter, "Seller") makes no other representations or warranties as to the insulation sold herein. The Seller disclaims all other warranties, express or implied, including the warranty of merchantability and the warranty of fitness for a particular purpose. Seller does, however, have a limited warranty as to the LTR-Value of the insulation, the terms of which are available upon request from the Seller. Seller shall not be liable for any incidental or consequential damages including but not limited to the cost of installation, removal, repair or replacement of this product. Buyer's remedies shall be limited exclusively to, at Seller's option, the repayment of the purchase price or resupply of product manufactured by Atlas in a quantity equal to that of the nonconforming product. Atlas distributors, agents, salespersons or other independent representatives have no authority to waive or alter the above limitation of liability and remedies.